

ARATA PES, NASCAR PRES, PHILIP PES

Estofos - Upholstery

TECHNICAL SPECIFICATIONS

CHARACTERISTICS	METHODS	UNITS	RESULTS
Weight	ISO 2286-2	g/m ²	640+/-5%
Thickness	ISO 2286-3	mm	0.95-1.15
Coating composition	---	%	PVC - 87
Textile composition	---	%	PES - 13
Tensile strength	ISO 1421	N	T / Warp>=400 Tr / Weft>=250
Elongation at break	ISO 1421	%	T / Warp>=45 Tr / Weft>=120
Tear strength	ISO 4674-1	N	T / Warp>=30 Tr / Weft>=35
Coating adhesion	ISO 2411	N/5cm	T / Warp>=40 Tr / Weft>=30
Abrasion resistance (Martindale)	ISO 5470-2	Cycles	400000 grade 2
Bally Flexion	ISO 5402	Cycles	150000
Colour fastness to rubbing (Crockmeter): dry/wet - 20 cycles	ISO 105-X12	Grey scale	4-5
Ethyl alcohol 96% vol. resistance	DIN 54021	Grey scale	4-5

Cleaning - Rub gently with a sponge or cloth moistened in a soapy water solution. Do not use multi-purpose products

REMARKS
SI 1243/195IG- Especificações Preliminares/ Preliminary Specifications

EDITION	REVISION
01. 29/01/2021	01. 05/05/2023

ARATA PES, NASCAR PRES, PHILIP PES

Estofos - Upholstery

TECHNICAL SPECIFICATIONS

CHARACTERISTICS	METHODS	UNITS	RESULTS
Bleach resistance (4.5% chlorine)	DIN 54021	Grey scale	4-5
Low temperature resistance - Cold crack (-30°C)	---	---	No crack
Colour fastness to saliva	DIN 53160-1	Grey scale	>=4
Resistance to artificial blood	---	Grey scale	>=4
Resistance ammoniac solution (urine)	---	Grey scale	>=4
Colour fastness to acid perspiration	ISO 105-E04	Grey scale	>=4
Colour fastness to alkaline perspiration	ISO 105-E04	Grey scale	>=4
Colour fastness to water	ISO 105-E01	Grey scale	>=4
Colour fastness to chlorinated water	ISO 105-E03	Grey scale	>=4
Colour fastness to sea water	ISO 105-E02	Grey scale	>=4
Bacterial resistance	JIS Z 2801	---	Sanitized ®
Fungal resistance	ISO 846 A	---	Sanitized ®

Cleaning - Rub gently with a sponge or cloth moistened in a soapy water solution. Do not use multi-purpose products

REMARKS
SI 1243/195IG- Especificações Preliminares/ Preliminary Specifications

EDITION	REVISION
01. 29/01/2021	01. 05/05/2023

ARATA PES, NASCAR PRES, PHILIP PES

Estofos - Upholstery

TECHNICAL SPECIFICATIONS

CHARACTERISTICS	METHODS	UNITS	RESULTS
Combustibility	FMVSS302	mm/min	<100
Burning behaviour EN 1021	EN 1021-1+2	---	Pass
Burning behaviour IMO 2010 FTP Code Part 8	IMO 2010 FTP Code Part 8	---	Pass
Burning Behaviour R118: annex:6	Regulation No.118	---	Pass
Burning Behaviour R118: annex:7	Regulation No.118	---	Pass
Burning Behaviour R118: annex:8	Regulation No.118	---	Pass
Burning behaviour Far 25.853	Far 25.853 Appendix F, Part. 1, paragraph (a) (1) (ii)	---	Pass
Fire resistance Cal. TB 117 – Section 1	California Technical Bulletin 117-section 1	---	Pass
Fire resistance NFPA 260 – 6.1	NFPA 260 – 6.1	---	Pass
Colour fastness to artificial weathering	ISO 105-B04	Blue scale	>=6
Light fastness	ISO 105-B02	---	>=6

Cleaning - Rub gently with a sponge or cloth moistened in a soapy water solution. Do not use multi-purpose products

REMARKS
SI 1243/195IG- Especificações Preliminares/ Preliminary Specifications

EDITION	REVISION
01. 29/01/2021	01. 05/05/2023